JFE Steel

철강사 강종 참고 자료

수록 데이터 요약

강종별 데이터 시트 수	59
공개 수치	590
공개 데이터의 주파수	50 Hz / 60 Hz
공개 자속 밀도 범위	1.5-1.7 T
자속 밀도 설정값 수	2

50 Hz 성능

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
1	**23JG110** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.70** W/kg	대표값
2	**23JG110** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**1.10** W/kg	보증 최댓값
3	**23JG110** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**1.00** W/kg	대표값
4	**23JGH090** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.63** W/kg	대표값
5	**23JGH090** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.90** W/kg	보증 최댓값
6	**23JGH090** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.88** W/kg	대표값
7	**23JGH095** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.64** W/kg	대표값
8	**23JGH095** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.95** W/kg	보증 최댓값
9	**23JGH095** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.91** W/kg	대표값
10	**23JGH100** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.66** W/kg	대표값
11	**23JGH100** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**1.00** W/kg	보증 최댓값
12	**23JGH100** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.95** W/kg	대표값
13	**23JGHE080** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.56** W/kg	대표값
14	**23JGHE080** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.80** W/kg	보증 최댓값
15	**23JGHE080** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.77** W/kg	대표값
16	**23JGHE085** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.57** W/kg	대표값
17	**23JGHE085** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.85** W/kg	보증 최댓값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
18	**23JGHE085** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.80** W/kg	대표값
19	**23JGS085** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.61** W/kg	대표값
20	**23JGS085** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.85** W/kg	보증 최댓값
21	**23JGS085** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.83** W/kg	대표값
22	**23JGS090** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.63** W/kg	대표값
23	**23JGS090** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.90** W/kg	보증 최댓값
24	**23JGS090** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.87** W/kg	대표값
25	**23JGS095** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.64** W/kg	대표값
26	**23JGS095** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.95** W/kg	보증 최댓값
27	**23JGS095** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.90** W/kg	대표값
28	**23JGSD075** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.53** W/kg	대표값
29	**23JGSD075** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.75** W/kg	보증 최댓값
30	**23JGSD075** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.72** W/kg	대표값
31	**23JGSD080** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.55** W/kg	대표값
32	**23JGSD080** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.80** W/kg	보증 최댓값
33	**23JGSD080** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.75** W/kg	대표값
34	**23JGSD085** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.57** W/kg	대표값
35	**23JGSD085** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.85** W/kg	보증 최댓값
36	**23JGSD085** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.78** W/kg	대표값
37	**23JGSE070** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.50** W/kg	대표값
38	**23JGSE070** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.70** W/kg	보증 최댓값
39	**23JGSE070** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.68** W/kg	대표값
40	**23JGSE075** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.52** W/kg	대표값
41	**23JGSE075** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.75** W/kg	보증 최댓값
42	**23JGSE075** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.72** W/kg	대표값
43	**23JGSE080** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.54** W/kg	대표값
44	**23JGSE080** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.80** W/kg	보증 최댓값
45	**23JGSE080** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.75** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
46	**27JG120** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.78** W/kg	대표값
47	**27JG120** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.20** W/kg	보증 최댓값
48	**27JG120** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.14** W/kg	대표값
49	**27JG130** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.83** W/kg	대표값
50	**27JG130** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.30** W/kg	보증 최댓값
51	**27JG130** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.23** W/kg	대표값
52	**27JGH100** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.71** W/kg	대표값
53	**27JGH100** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.00** W/kg	보증 최댓값
54	**27JGH100** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.98** W/kg	대표값
55	**27JGH110** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.74** W/kg	대표값
56	**27JGH110** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.10** W/kg	보증 최댓값
57	**27JGH110** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.03** W/kg	대표값
58	**27JGS090** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.66** W/kg	대표값
59	**27JGS090** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.90** W/kg	보증 최댓값
60	**27JGS090** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.88** W/kg	대표값
61	**27JGS095** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.69** W/kg	대표값
62	**27JGS095** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.95** W/kg	보증 최댓값
63	**27JGS095** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.92** W/kg	대표값
64	**27JGS100** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.70** W/kg	대표값
65	**27JGS100** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.00** W/kg	보증 최댓값
66	**27JGS100** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.95** W/kg	대표값
67	**27JGSD090** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.62** W/kg	대표값
68	**27JGSD090** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.90** W/kg	보증 최댓값
69	**27JGSD090** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.84** W/kg	대표값
70	**27JGSD095** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.65** W/kg	대표값
71	**27JGSD095** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.95** W/kg	보증 최댓값
72	**27JGSD095** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.88** W/kg	대표값
73	**27JGSE085** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.61** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
74	**27JGSE085** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.85** W/kg	보증 최댓값
75	**27JGSE085** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.81** W/kg	대표값
76	**27JGSE090** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.63** W/kg	대표값
77	**27JGSE090** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.90** W/kg	보증 최댓값
78	**27JGSE090** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**0.84** W/kg	대표값
79	**30JG120** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.83** W/kg	대표값
80	**30JG120** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.20** W/kg	보증 최댓값
81	**30JG120** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.17** W/kg	대표값
82	**30JG130** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.87** W/kg	대표값
83	**30JG130** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.30** W/kg	보증 최댓값
84	**30JG130** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.24** W/kg	대표값
85	**30JG140** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.90** W/kg	대표값
86	**30JG140** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.40** W/kg	보증 최댓값
87	**30JG140** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.32** W/kg	대표값
88	**30JGH105** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.75** W/kg	대표값
89	**30JGH105** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.05** W/kg	보증 최댓값
90	**30JGH105** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.03** W/kg	대표값
91	**30JGH110** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.78** W/kg	대표값
92	**30JGH110** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.10** W/kg	보증 최댓값
93	**30JGH110** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.07** W/kg	대표값
94	**30JGH120** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.83** W/kg	대표값
95	**30JGH120** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.20** W/kg	보증 최댓값
96	**30JGH120** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.14** W/kg	대표값
97	**30JGS095** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.70** W/kg	대표값
98	**30JGS095** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**0.95** W/kg	보증 최댓값
99	**30JGS095** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**0.93** W/kg	대표값
100	**30JGS100** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.72** W/kg	대표값
101	**30JGS100** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.00** W/kg	보증 최댓값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
102	**30JGS100** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**0.96** W/kg	대표값
103	**30JGS105** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.75** W/kg	대표값
104	**30JGS105** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.05** W/kg	보증 최댓값
105	**30JGS105** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.00** W/kg	대표값
106	**35JG135** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.95** W/kg	대표값
107	**35JG135** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.35** W/kg	보증 최댓값
108	**35JG135** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.33** W/kg	대표값
109	**35JG145** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.98** W/kg	대표값
110	**35JG145** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.45** W/kg	보증 최댓값
111	**35JG145** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.38** W/kg	대표값
112	**35JG155** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**1.02** W/kg	대표값
113	**35JG155** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.55** W/kg	보증 최댓값
114	**35JG155** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.47** W/kg	대표값
115	**35JGH115** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.86** W/kg	대표값
116	**35JGH115** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.15** W/kg	보증 최댓값
117	**35JGH115** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.13** W/kg	대표값
118	**35JGH125** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.89** W/kg	대표값
119	**35JGH125** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.25** W/kg	보증 최댓값
120	**35JGH125** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.22** W/kg	대표값
121	**35JGH135** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.91** W/kg	대표값
122	**35JGH135** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.35** W/kg	보증 최댓값
123	**35JGH135** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.26** W/kg	대표값
124	**35JGS115** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.84** W/kg	대표값
125	**35JGS115** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.15** W/kg	보증 최댓값
126	**35JGS115** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.10** W/kg	대표값
127	**35JGS125** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.91** W/kg	대표값
128	**35JGS125** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.25** W/kg	보증 최댓값
129	**35JGS125** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.20** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
130	**M-0H** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.67** W/kg	보증 최댓값
131	**M-0H** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.65** W/kg	대표값
132	**M-0H** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**1.00** W/kg	보증 최댓값
133	**M-0H** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**0.93** W/kg	대표값
134	**M-0H** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.73** W/kg	보증 최댓값
135	**M-0H** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.72** W/kg	대표값
136	**M-0H** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.03** W/kg	보증 최댓값
137	**M-0H** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.01** W/kg	대표값
138	**M-0H** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.76** W/kg	보증 최댓값
139	**M-0H** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.75** W/kg	대표값
140	**M-0H** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.05** W/kg	보증 최댓값
141	**M-0H** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.04** W/kg	대표값
142	**M-1H** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.77** W/kg	보증 최댓값
143	**M-1H** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.74** W/kg	대표값
144	**M-1H** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.09** W/kg	보증 최댓값
145	**M-1H** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.05** W/kg	대표값
146	**M-1H** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.80** W/kg	보증 최댓값
147	**M-1H** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.78** W/kg	대표값
148	**M-1H** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.11** W/kg	보증 최댓값
149	**M-1H** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.08** W/kg	대표값
150	**M-1H** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.87** W/kg	보증 최댓값
151	**M-1H** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.86** W/kg	대표값
152	**M-1H** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.16** W/kg	보증 최댓값
153	**M-1H** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.14** W/kg	대표값
154	**M-2H** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.85** W/kg	보증 최댓값
155	**M-2H** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.81** W/kg	대표값
156	**M-2H** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.17** W/kg	보증 최댓값
157	**M-2H** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.13** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
158	**M-2H** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.90** W/kg	보증 최댓값
159	**M-2H** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.88** W/kg	대표값
160	**M-2H** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.22** W/kg	보증 최댓값
161	**M-2H** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.20** W/kg	대표값
162	**M-3** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.79** W/kg	보증 최댓값
163	**M-3** JFE Steel	0.23	비철손	50 Hz / 1.5 T (J)	**0.70** W/kg	대표값
164	**M-3** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**1.18** W/kg	보증 최댓값
165	**M-3** JFE Steel	0.23	비철손	50 Hz / 1.7 T (J)	**1.00** W/kg	대표값
166	**M-3** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.83** W/kg	보증 최댓값
167	**M-3** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.80** W/kg	대표값
168	**M-3** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.21** W/kg	보증 최댓값
169	**M-3** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.17** W/kg	대표값
170	**M-3H** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.96** W/kg	보증 최댓값
171	**M-3H** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.90** W/kg	대표값
172	**M-3H** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.28** W/kg	보증 최댓값
173	**M-3H** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.24** W/kg	대표값
174	**M-4** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.89** W/kg	보증 최댓값
175	**M-4** JFE Steel	0.27	비철손	50 Hz / 1.5 T (J)	**0.82** W/kg	대표값
176	**M-4** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.27** W/kg	보증 최댓값
177	**M-4** JFE Steel	0.27	비철손	50 Hz / 1.7 T (J)	**1.22** W/kg	대표값
178	**M-4** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.90** W/kg	보증 최댓값
179	**M-4** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.87** W/kg	대표값
180	**M-4** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.32** W/kg	보증 최댓값
181	**M-4** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.24** W/kg	대표값
182	**M-5** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.97** W/kg	보증 최댓값
183	**M-5** JFE Steel	0.3	비철손	50 Hz / 1.5 T (J)	**0.90** W/kg	대표값
184	**M-5** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.39** W/kg	보증 최댓값
185	**M-5** JFE Steel	0.3	비철손	50 Hz / 1.7 T (J)	**1.32** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
186	**M-5** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**1.01** W/kg	보증 최댓값
187	**M-5** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**0.97** W/kg	대표값
188	**M-5** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.45** W/kg	보증 최댓값
189	**M-5** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.36** W/kg	대표값
190	**M-6** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**1.11** W/kg	보증 최댓값
191	**M-6** JFE Steel	0.35	비철손	50 Hz / 1.5 T (J)	**1.02** W/kg	대표값
192	**M-6** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.57** W/kg	보증 최댓값
193	**M-6** JFE Steel	0.35	비철손	50 Hz / 1.7 T (J)	**1.47** W/kg	대표값

60 Hz 성능

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
194	**23JG110** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.93** W/kg	대표값
195	**23JG110** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.45** W/kg	보증 최댓값
196	**23JG110** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.30** W/kg	대표값
197	**23JGH090** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.81** W/kg	대표값
198	**23JGH090** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.19** W/kg	보증 최댓값
199	**23JGH090** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.15** W/kg	대표값
200	**23JGH095** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.84** W/kg	대표값
201	**23JGH095** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.25** W/kg	보증 최댓값
202	**23JGH095** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.19** W/kg	대표값
203	**23JGH100** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.86** W/kg	대표값
204	**23JGH100** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.32** W/kg	보증 최댓값
205	**23JGH100** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.23** W/kg	대표값
206	**23JGHE080** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.74** W/kg	대표값
207	**23JGHE080** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.05** W/kg	보증 최댓값
208	**23JGHE080** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.01** W/kg	대표값
209	**23JGHE085** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.75** W/kg	대표값
210	**23JGHE085** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.12** W/kg	보증 최댓값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
211	**23JGHE085** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.04** W/kg	대표값
212	**23JGS085** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.80** W/kg	대표값
213	**23JGS085** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.12** W/kg	보증 최댓값
214	**23JGS085** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.09** W/kg	대표값
215	**23JGS090** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.82** W/kg	대표값
216	**23JGS090** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.19** W/kg	보증 최댓값
217	**23JGS090** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.12** W/kg	대표값
218	**23JGS095** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.83** W/kg	대표값
219	**23JGS095** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.25** W/kg	보증 최댓값
220	**23JGS095** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.16** W/kg	대표값
221	**23JGSD075** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.71** W/kg	대표값
222	**23JGSD075** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**0.99** W/kg	보증 최댓값
223	**23JGSD075** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**0.95** W/kg	대표값
224	**23JGSD080** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.73** W/kg	대표값
225	**23JGSD080** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.04** W/kg	보증 최댓값
226	**23JGSD080** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**0.97** W/kg	대표값
227	**23JGSD085** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.75** W/kg	대표값
228	**23JGSD085** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.12** W/kg	보증 최댓값
229	**23JGSD085** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.02** W/kg	대표값
230	**23JGSE070** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.66** W/kg	대표값
231	**23JGSE070** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**0.91** W/kg	보증 최댓값
232	**23JGSE070** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**0.89** W/kg	대표값
233	**23JGSE075** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.70** W/kg	대표값
234	**23JGSE075** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**0.99** W/kg	보증 최댓값
235	**23JGSE075** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**0.95** W/kg	대표값
236	**23JGSE080** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.72** W/kg	대표값
237	**23JGSE080** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.05** W/kg	보증 최댓값
238	**23JGSE080** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**0.98** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
239	**27JG120** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**1.01** W/kg	대표값
240	**27JG120** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.58** W/kg	보증 최댓값
241	**27JG120** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.47** W/kg	대표값
242	**27JG130** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**1.08** W/kg	대표값
243	**27JG130** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.72** W/kg	보증 최댓값
244	**27JG130** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.59** W/kg	대표값
245	**27JGH100** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.93** W/kg	대표값
246	**27JGH100** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.32** W/kg	보증 최댓값
247	**27JGH100** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.30** W/kg	대표값
248	**27JGH110** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.97** W/kg	대표값
249	**27JGH110** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.45** W/kg	보증 최댓값
250	**27JGH110** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.34** W/kg	대표값
251	**27JGS090** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.87** W/kg	대표값
252	**27JGS090** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.19** W/kg	보증 최댓값
253	**27JGS090** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.16** W/kg	대표값
254	**27JGS095** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.91** W/kg	대표값
255	**27JGS095** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.25** W/kg	보증 최댓값
256	**27JGS095** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.22** W/kg	대표값
257	**27JGS100** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.94** W/kg	대표값
258	**27JGS100** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.32** W/kg	보증 최댓값
259	**27JGS100** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.25** W/kg	대표값
260	**27JGSD090** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.82** W/kg	대표값
261	**27JGSD090** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.18** W/kg	보증 최댓값
262	**27JGSD090** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.11** W/kg	대표값
263	**27JGSD095** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.85** W/kg	대표값
264	**27JGSD095** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.25** W/kg	보증 최댓값
265	**27JGSD095** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.16** W/kg	대표값
266	**27JGSE085** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.82** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
267	**27JGSE085** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.13** W/kg	보증 최댓값
268	**27JGSE085** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.08** W/kg	대표값
269	**27JGSE090** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.84** W/kg	대표값
270	**27JGSE090** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.19** W/kg	보증 최댓값
271	**27JGSE090** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.12** W/kg	대표값
272	**30JG120** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.10** W/kg	대표값
273	**30JG120** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.58** W/kg	보증 최댓값
274	**30JG120** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.54** W/kg	대표값
275	**30JG130** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.15** W/kg	대표값
276	**30JG130** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.72** W/kg	보증 최댓값
277	**30JG130** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.63** W/kg	대표값
278	**30JG140** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.19** W/kg	대표값
279	**30JG140** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.85** W/kg	보증 최댓값
280	**30JG140** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.71** W/kg	대표값
281	**30JGH105** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**0.97** W/kg	대표값
282	**30JGH105** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.39** W/kg	보증 최댓값
283	**30JGH105** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.36** W/kg	대표값
284	**30JGH110** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.01** W/kg	대표값
285	**30JGH110** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.45** W/kg	보증 최댓값
286	**30JGH110** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.41** W/kg	대표값
287	**30JGH120** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.10** W/kg	대표값
288	**30JGH120** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.58** W/kg	보증 최댓값
289	**30JGH120** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.50** W/kg	대표값
290	**30JGS095** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**0.93** W/kg	대표값
291	**30JGS095** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.27** W/kg	보증 최댓값
292	**30JGS095** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.25** W/kg	대표값
293	**30JGS100** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**0.96** W/kg	대표값
294	**30JGS100** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.32** W/kg	보증 최댓값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
295	**30JGS100** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.27** W/kg	대표값
296	**30JGS105** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**0.99** W/kg	대표값
297	**30JGS105** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.39** W/kg	보증 최댓값
298	**30JGS105** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.29** W/kg	대표값
299	**35JG135** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.26** W/kg	대표값
300	**35JG135** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.78** W/kg	보증 최댓값
301	**35JG135** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.76** W/kg	대표값
302	**35JG145** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.30** W/kg	대표값
303	**35JG145** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.91** W/kg	보증 최댓값
304	**35JG145** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.81** W/kg	대표값
305	**35JG155** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.34** W/kg	대표값
306	**35JG155** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**2.04** W/kg	보증 최댓값
307	**35JG155** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.92** W/kg	대표값
308	**35JGH115** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.15** W/kg	대표값
309	**35JGH115** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.52** W/kg	보증 최댓값
310	**35JGH115** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.53** W/kg	대표값
311	**35JGH125** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.19** W/kg	대표값
312	**35JGH125** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.65** W/kg	보증 최댓값
313	**35JGH125** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.60** W/kg	대표값
314	**35JGH135** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.21** W/kg	대표값
315	**35JGH135** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.78** W/kg	보증 최댓값
316	**35JGH135** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.65** W/kg	대표값
317	**35JGS115** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.11** W/kg	대표값
318	**35JGS115** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.52** W/kg	보증 최댓값
319	**35JGS115** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.47** W/kg	대표값
320	**35JGS125** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.20** W/kg	대표값
321	**35JGS125** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.65** W/kg	보증 최댓값
322	**35JGS125** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.60** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
323	**M-0H** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.88** W/kg	보증 최댓값
324	**M-0H** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.85** W/kg	대표값
325	**M-0H** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.32** W/kg	보증 최댓값
326	**M-0H** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.20** W/kg	대표값
327	**M-0H** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.95** W/kg	보증 최댓값
328	**M-0H** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.95** W/kg	대표값
329	**M-0H** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.36** W/kg	보증 최댓값
330	**M-0H** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.32** W/kg	대표값
331	**M-0H** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**0.99** W/kg	보증 최댓값
332	**M-0H** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**0.99** W/kg	대표값
333	**M-0H** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.39** W/kg	보증 최댓값
334	**M-0H** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.37** W/kg	대표값
335	**M-1H** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**1.01** W/kg	보증 최댓값
336	**M-1H** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**0.97** W/kg	대표값
337	**M-1H** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.44** W/kg	보증 최댓값
338	**M-1H** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.37** W/kg	대표값
339	**M-1H** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.06** W/kg	보증 최댓값
340	**M-1H** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.01** W/kg	대표값
341	**M-1H** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.45** W/kg	보증 최댓값
342	**M-1H** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.41** W/kg	대표값
343	**M-1H** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.15** W/kg	보증 최댓값
344	**M-1H** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.14** W/kg	대표값
345	**M-1H** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.53** W/kg	보증 최댓값
346	**M-1H** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.54** W/kg	대표값
347	**M-2H** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.15** W/kg	보증 최댓값
348	**M-2H** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.06** W/kg	대표값
349	**M-2H** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.54** W/kg	보증 최댓값
350	**M-2H** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.50** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
351	**M-2H** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.19** W/kg	보증 최댓값
352	**M-2H** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.17** W/kg	대표값
353	**M-2H** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.59** W/kg	보증 최댓값
354	**M-2H** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.59** W/kg	대표값
355	**M-3** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**1.04** W/kg	보증 최댓값
356	**M-3** JFE Steel	0.23	비철손	60 Hz / 1.5 T (J)	**0.93** W/kg	대표값
357	**M-3** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.55** W/kg	보증 최댓값
358	**M-3** JFE Steel	0.23	비철손	60 Hz / 1.7 T (J)	**1.30** W/kg	대표값
359	**M-3** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**1.09** W/kg	보증 최댓값
360	**M-3** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**1.06** W/kg	대표값
361	**M-3** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.59** W/kg	보증 최댓값
362	**M-3** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.52** W/kg	대표값
363	**M-3H** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.28** W/kg	보증 최댓값
364	**M-3H** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.19** W/kg	대표값
365	**M-3H** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.68** W/kg	보증 최댓값
366	**M-3H** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.63** W/kg	대표값
367	**M-4** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**1.17** W/kg	보증 최댓값
368	**M-4** JFE Steel	0.27	비철손	60 Hz / 1.5 T (J)	**1.08** W/kg	대표값
369	**M-4** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.68** W/kg	보증 최댓값
370	**M-4** JFE Steel	0.27	비철손	60 Hz / 1.7 T (J)	**1.59** W/kg	대표값
371	**M-4** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.19** W/kg	보증 최댓값
372	**M-4** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.15** W/kg	대표값
373	**M-4** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.74** W/kg	보증 최댓값
374	**M-4** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.63** W/kg	대표값
375	**M-5** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.28** W/kg	보증 최댓값
376	**M-5** JFE Steel	0.3	비철손	60 Hz / 1.5 T (J)	**1.19** W/kg	대표값
377	**M-5** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.83** W/kg	보증 최댓값
378	**M-5** JFE Steel	0.3	비철손	60 Hz / 1.7 T (J)	**1.71** W/kg	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
379	**M-5** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.32** W/kg	보증 최댓값
380	**M-5** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.30** W/kg	대표값
381	**M-5** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.91** W/kg	보증 최댓값
382	**M-5** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.79** W/kg	대표값
383	**M-6** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.46** W/kg	보증 최댓값
384	**M-6** JFE Steel	0.35	비철손	60 Hz / 1.5 T (J)	**1.34** W/kg	대표값
385	**M-6** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**2.07** W/kg	보증 최댓값
386	**M-6** JFE Steel	0.35	비철손	60 Hz / 1.7 T (J)	**1.92** W/kg	대표값

기타 특성

주파수 별도 표기 없음

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
387	**23JG110** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.76** T	대표값
388	**23JG110** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
389	**23JG110** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.85** T	대표값
390	**23JG110** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.92** T	대표값
391	**23JGH090** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.81** T	대표값
392	**23JGH090** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
393	**23JGH090** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.89** T	대표값
394	**23JGH090** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.94** T	대표값
395	**23JGH095** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.81** T	대표값
396	**23JGH095** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
397	**23JGH095** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.89** T	대표값
398	**23JGH095** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.94** T	대표값
399	**23JGH100** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.81** T	대표값
400	**23JGH100** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
401	**23JGH100** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.89** T	대표값
402	**23JGH100** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.94** T	대표값
403	**23JGHE080** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.85** T	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
404	**23JGHE080** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
405	**23JGHE080** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.91** T	대표값
406	**23JGHE080** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.96** T	대표값
407	**23JGHE085** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.84** T	대표값
408	**23JGHE085** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
409	**23JGHE085** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.89** T	대표값
410	**23JGHE085** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.94** T	대표값
411	**23JGS085** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.89** T	대표값
412	**23JGS085** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
413	**23JGS085** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.93** T	대표값
414	**23JGS085** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.97** T	대표값
415	**23JGS090** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.89** T	대표값
416	**23JGS090** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
417	**23JGS090** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.92** T	대표값
418	**23JGS090** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.97** T	대표값
419	**23JGS095** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.89** T	대표값
420	**23JGS095** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
421	**23JGS095** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.92** T	대표값
422	**23JGS095** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.97** T	대표값
423	**23JGSD075** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.84** T	대표값
424	**23JGSD075** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
425	**23JGSD075** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.89** T	대표값
426	**23JGSD075** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.94** T	대표값
427	**23JGSD080** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.83** T	대표값
428	**23JGSD080** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
429	**23JGSD080** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.89** T	대표값
430	**23JGSD080** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.94** T	대표값
431	**23JGSD085** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.82** T	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
432	**23JGSD085** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
433	**23JGSD085** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.89** T	대표값
434	**23JGSD085** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.94** T	대표값
435	**23JGSE070** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.89** T	대표값
436	**23JGSE070** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
437	**23JGSE070** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.93** T	대표값
438	**23JGSE070** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.97** T	대표값
439	**23JGSE075** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.89** T	대표값
440	**23JGSE075** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
441	**23JGSE075** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.92** T	대표값
442	**23JGSE075** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.97** T	대표값
443	**23JGSE080** JFE Steel	0.23	자기 분극	H = 300 A/m	**1.89** T	대표값
444	**23JGSE080** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
445	**23JGSE080** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.92** T	대표값
446	**23JGSE080** JFE Steel	0.23	자기 분극	H = 2500 A/m	**1.97** T	대표값
447	**27JG120** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.76** T	대표값
448	**27JG120** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
449	**27JG120** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.85** T	대표값
450	**27JG120** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.92** T	대표값
451	**27JG130** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.74** T	대표값
452	**27JG130** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
453	**27JG130** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.84** T	대표값
454	**27JG130** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.91** T	대표값
455	**27JGH100** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.81** T	대표값
456	**27JGH100** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
457	**27JGH100** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.89** T	대표값
458	**27JGH100** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.94** T	대표값
459	**27JGH110** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.81** T	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
460	**27JGH110** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
461	**27JGH110** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.89** T	대표값
462	**27JGH110** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.94** T	대표값
463	**27JGS090** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.91** T	대표값
464	**27JGS090** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
465	**27JGS090** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.94** T	대표값
466	**27JGS090** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.98** T	대표값
467	**27JGS095** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.90** T	대표값
468	**27JGS095** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
469	**27JGS095** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.93** T	대표값
470	**27JGS095** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.98** T	대표값
471	**27JGS100** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.90** T	대표값
472	**27JGS100** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
473	**27JGS100** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.93** T	대표값
474	**27JGS100** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.98** T	대표값
475	**27JGSD090** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.84** T	대표값
476	**27JGSD090** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
477	**27JGSD090** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.89** T	대표값
478	**27JGSD090** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.94** T	대표값
479	**27JGSD095** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.84** T	대표값
480	**27JGSD095** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
481	**27JGSD095** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.89** T	대표값
482	**27JGSD095** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.94** T	대표값
483	**27JGSE085** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.90** T	대표값
484	**27JGSE085** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
485	**27JGSE085** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.93** T	대표값
486	**27JGSE085** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.98** T	대표값
487	**27JGSE090** JFE Steel	0.27	자기 분극	H = 300 A/m	**1.90** T	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
488	**27JGSE090** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
489	**27JGSE090** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.93** T	대표값
490	**27JGSE090** JFE Steel	0.27	자기 분극	H = 2500 A/m	**1.98** T	대표값
491	**30JG120** JFE Steel	0.3	자기 분극	H = 300 A/m	**1.76** T	대표값
492	**30JG120** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
493	**30JG120** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.85** T	대표값
494	**30JG120** JFE Steel	0.3	자기 분극	H = 2500 A/m	**1.92** T	대표값
495	**30JG130** JFE Steel	0.3	자기 분극	H = 300 A/m	**1.74** T	대표값
496	**30JG130** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
497	**30JG130** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.84** T	대표값
498	**30JG130** JFE Steel	0.3	자기 분극	H = 2500 A/m	**1.91** T	대표값
499	**30JG140** JFE Steel	0.3	자기 분극	H = 300 A/m	**1.73** T	대표값
500	**30JG140** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
501	**30JG140** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.83** T	대표값
502	**30JG140** JFE Steel	0.3	자기 분극	H = 2500 A/m	**1.91** T	대표값
503	**30JGH105** JFE Steel	0.3	자기 분극	H = 300 A/m	**1.82** T	대표값
504	**30JGH105** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
505	**30JGH105** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.89** T	대표값
506	**30JGH105** JFE Steel	0.3	자기 분극	H = 2500 A/m	**1.94** T	대표값
507	**30JGH110** JFE Steel	0.3	자기 분극	H = 300 A/m	**1.82** T	대표값
508	**30JGH110** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
509	**30JGH110** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.89** T	대표값
510	**30JGH110** JFE Steel	0.3	자기 분극	H = 2500 A/m	**1.94** T	대표값
511	**30JGH120** JFE Steel	0.3	자기 분극	H = 300 A/m	**1.82** T	대표값
512	**30JGH120** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
513	**30JGH120** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.89** T	대표값
514	**30JGH120** JFE Steel	0.3	자기 분극	H = 2500 A/m	**1.94** T	대표값
515	**30JGS095** JFE Steel	0.3	자기 분극	H = 300 A/m	**1.92** T	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
516	**30JGS095** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
517	**30JGS095** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.95** T	대표값
518	**30JGS095** JFE Steel	0.3	자기 분극	H = 2500 A/m	**1.98** T	대표값
519	**30JGS100** JFE Steel	0.3	자기 분극	H = 300 A/m	**1.91** T	대표값
520	**30JGS100** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
521	**30JGS100** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.94** T	대표값
522	**30JGS100** JFE Steel	0.3	자기 분극	H = 2500 A/m	**1.98** T	대표값
523	**30JGS105** JFE Steel	0.3	자기 분극	H = 300 A/m	**1.90** T	대표값
524	**30JGS105** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
525	**30JGS105** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.93** T	대표값
526	**30JGS105** JFE Steel	0.3	자기 분극	H = 2500 A/m	**1.98** T	대표값
527	**35JG135** JFE Steel	0.35	자기 분극	H = 300 A/m	**1.77** T	대표값
528	**35JG135** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
529	**35JG135** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.85** T	대표값
530	**35JG135** JFE Steel	0.35	자기 분극	H = 2500 A/m	**1.91** T	대표값
531	**35JG145** JFE Steel	0.35	자기 분극	H = 300 A/m	**1.76** T	대표값
532	**35JG145** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
533	**35JG145** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.84** T	대표값
534	**35JG145** JFE Steel	0.35	자기 분극	H = 2500 A/m	**1.91** T	대표값
535	**35JG155** JFE Steel	0.35	자기 분극	H = 300 A/m	**1.74** T	대표값
536	**35JG155** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
537	**35JG155** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.83** T	대표값
538	**35JG155** JFE Steel	0.35	자기 분극	H = 2500 A/m	**1.90** T	대표값
539	**35JGH115** JFE Steel	0.35	자기 분극	H = 300 A/m	**1.83** T	대표값
540	**35JGH115** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
541	**35JGH115** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.89** T	대표값
542	**35JGH115** JFE Steel	0.35	자기 분극	H = 2500 A/m	**1.96** T	대표값
543	**35JGH125** JFE Steel	0.35	자기 분극	H = 300 A/m	**1.83** T	대표값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
544	**35JGH125** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
545	**35JGH125** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.89** T	대표값
546	**35JGH125** JFE Steel	0.35	자기 분극	H = 2500 A/m	**1.96** T	대표값
547	**35JGH135** JFE Steel	0.35	자기 분극	H = 300 A/m	**1.83** T	대표값
548	**35JGH135** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
549	**35JGH135** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.89** T	대표값
550	**35JGH135** JFE Steel	0.35	자기 분극	H = 2500 A/m	**1.96** T	대표값
551	**35JGS115** JFE Steel	0.35	자기 분극	H = 300 A/m	**1.90** T	대표값
552	**35JGS115** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
553	**35JGS115** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.93** T	대표값
554	**35JGS115** JFE Steel	0.35	자기 분극	H = 2500 A/m	**1.98** T	대표값
555	**35JGS125** JFE Steel	0.35	자기 분극	H = 300 A/m	**1.89** T	대표값
556	**35JGS125** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.90** T	보증 최솟값
557	**35JGS125** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.92** T	대표값
558	**35JGS125** JFE Steel	0.35	자기 분극	H = 2500 A/m	**1.97** T	대표값
559	**M-0H** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.87** T	보증 최솟값
560	**M-0H** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.89** T	대표값
561	**M-0H** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
562	**M-0H** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.89** T	대표값
563	**M-0H** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
564	**M-0H** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.89** T	대표값
565	**M-1H** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
566	**M-1H** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.89** T	대표값
567	**M-1H** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
568	**M-1H** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.89** T	대표값
569	**M-1H** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
570	**M-1H** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.89** T	대표값
571	**M-2H** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값

번호	철강사 / 강종	두께 mm	특성	시험점	수치	값 구분
572	**M-2H** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.89** T	대표값
573	**M-2H** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
574	**M-2H** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.89** T	대표값
575	**M-3** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
576	**M-3** JFE Steel	0.23	자기 분극	H = 800 A/m	**1.85** T	대표값
577	**M-3** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
578	**M-3** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.85** T	대표값
579	**M-3H** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.88** T	보증 최솟값
580	**M-3H** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.89** T	대표값
581	**M-4** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
582	**M-4** JFE Steel	0.27	자기 분극	H = 800 A/m	**1.84** T	대표값
583	**M-4** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
584	**M-4** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.85** T	대표값
585	**M-5** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
586	**M-5** JFE Steel	0.3	자기 분극	H = 800 A/m	**1.84** T	대표값
587	**M-5** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
588	**M-5** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.84** T	대표값
589	**M-6** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.80** T	보증 최솟값
590	**M-6** JFE Steel	0.35	자기 분극	H = 800 A/m	**1.83** T	대표값

제조사 출처와 시험 조건

표와 행 번호를 사용해 원문 시험 조건을 확인하세요.

JFE Steel

Electrical Steel Sheets

개정 정보 Cat. No. F1E-001-08; footer code 2003R(1903) JTR 공식 문서

PDF 8페이지 · 데이터 행 1, 3, 46, 48-49, 51, 79, 81-82, 84-85, 87, 106, 108-109, 111-112, 114, 194, 196, 239, 241-242, 244, 272, 274-275, 277-278, 280, 299, 301-302, 304-305, 307, 387, 389-390, 447, 449-451, 453-454, 491, 493-495, 497-499, 501-502, 527, 529-531, 533-535, 537-538

출처 페이지 및 시험 방법 JG CORE: Typical Electrical and Magnetic Properties · 시험 조건은 출처 참조

시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed.

PDF 6페이지 · 데이터 행 2, 47, 50, 80, 83, 86, 107, 110, 113, 195, 240, 243, 273, 276, 279, 300, 303, 306, 388, 448, 452, 492, 496, 500, 528, 532, 536

출처 페이지 및 시험 방법 JG CORE: Grades and Specifications · 시험 조건은 출처 참조

시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed.

PDF 8페이지 · 데이터 행 4, 6-7, 9-10, 12, 52, 54-55, 57, 88, 90-91, 93-94, 96, 115, 117-118, 120-121, 123, 197, 199-200, 202-203, 205, 245, 247-248, 250, 281, 283-284, 286-287, 289, 308, 311, 313-314, 316, 391, 393-395, 397-399, 401-402, 455, 457-459, 461-462, 503, 505-507, 509-511, 513-514, 539, 541-543, 545-547, 549-550

출처 페이지 및 시험 방법 JGH CORE: Typical Electrical and Magnetic Properties · 시험 조건은 출처 참조

시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed.

PDF 6페이지 · 데이터 행 5, 8, 11, 53, 56, 89, 92, 95, 116, 119, 122, 198, 201, 204, 246, 249, 282, 285, 288, 312, 315, 392, 396, 400, 456, 460, 504, 508, 512, 540, 544, 548

출처 페이지 및 시험 방법 JGH CORE: Grades and Specifications · 시험 조건은 출처 참조

시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed.

PDF 8페이지 · 데이터 행 13, 15-16, 18, 206, 208-209, 211, 403, 405-407, 409-410

출처 페이지 및 시험 방법 JGHE CORE: Typical Electrical and Magnetic Properties · 시험 조건은 출처 참조

시험 조건 설명(영어) JIS C 2556:2015 / IEC 60404-3:2010, single-sheet tester; specimens sheared parallel to rolling direction without stress-relief annealing.

PDF 6페이지 · 데이터 행 14, 17, 207, 210, 404, 408

출처 페이지 및 시험 방법 JGHE CORE: Grades and Specifications · 시험 조건은 출처 참조

시험 조건 설명(영어) JIS C 2556:2015 / IEC 60404-3:2010, single-sheet tester; specimens sheared parallel to rolling direction without stress-relief annealing.

PDF 9페이지 · 데이터 행 19, 21-22, 24-25, 27, 58, 60-61, 63-64, 66, 97, 99-100, 102-103, 105, 124, 126-127, 129, 212, 214-215, 217-218, 220, 251, 253-254, 256-257, 259, 290, 292-293, 295-296, 298, 317, 319-320, 322, 411, 413-415, 417-419, 421-422, 463, 465-467, 469-471, 473-474, 515, 517-519, 521-523, 525-526, 551, 553-555, 557-558

출처 페이지 및 시험 방법 JGS CORE: Typical Electrical and Magnetic Properties · 시험 조건은 출처 참조

시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed.

PDF 7페이지 · 데이터 행 20, 23, 26, 59, 62, 65, 98, 101, 104, 125, 128, 213, 216, 219, 252, 255, 258, 291, 294, 297, 318, 321, 412, 416, 420, 464, 468, 472, 516, 520, 524, 552, 556

출처 페이지 및 시험 방법 JGS CORE: Grades and Specifications · 시험 조건은 출처 참조

시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed.

PDF 9페이지 · 데이터 행 28, 30-31, 33-34, 36, 67, 69-70, 72, 221, 223-224, 226-227, 229, 260, 262-263, 265, 423, 425-427, 429-431, 433-434, 475, 477-479, 481-482

출처 페이지 및 시험 방법 JGSD CORE: Typical Electrical and Magnetic Properties · 시험 조건은 출처 참조

시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed.

PDF 7페이지 · **데이터 행 29, 32, 35, 68, 71, 222, 225, 228, 261, 264, 424, 428, 432, 476, 480**
출처 페이지 및 시험 방법 JGSD CORE: Grades and Specifications · 시험 조건은 출처 참조
시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed.

PDF 9페이지 · **데이터 행 37, 39-40, 42-43, 45, 73, 75-76, 78, 230, 232-233, 235-236, 238, 266, 268-269, 271, 435, 437-439, 441-443, 445-446, 483, 485-487, 489-490**
출처 페이지 및 시험 방법 JGSE CORE: Typical Electrical and Magnetic Properties · 시험 조건은 출처 참조
시험 조건 설명(영어) JIS C 2556:2015 / IEC 60404-3:2010, single-sheet tester; specimens sheared parallel to rolling direction without stress-relief annealing.

PDF 7페이지 · **데이터 행 38, 41, 44, 74, 77, 231, 234, 237, 267, 270, 436, 440, 444, 484, 488**
출처 페이지 및 시험 방법 JGSE CORE: Grades and Specifications · 시험 조건은 출처 참조
시험 조건 설명(영어) JIS C 2556:2015 / IEC 60404-3:2010, single-sheet tester; specimens sheared parallel to rolling direction without stress-relief annealing.

PDF 10페이지 · **데이터 행 130, 132, 134, 136, 138, 140, 142, 144, 146, 148, 150, 152, 154, 156, 158, 160, 162, 164, 166, 168, 170, 172, 174, 176, 178, 180, 182, 184, 186, 188, 190, 192, 323, 325, 327, 329, 331, 333, 335, 337, 339, 341, 343, 347, 349, 351, 353, 355, 357, 359, 361, 363, 365, 367, 369, 371, 373, 375, 377, 379, 381, 383, 385, 559, 561, 563, 565, 567, 569, 571, 573, 575, 577, 579, 581, 583, 585, 587, 589**
출처 페이지 및 시험 방법 AISI: Grades and Specifications · 시험 조건은 출처 참조
시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343), rolling-direction specimens, stress-relief annealed; AISI section.

PDF 11페이지 · **데이터 행 131, 133, 135, 137, 139, 141, 143, 145, 147, 149, 151, 153, 155, 157, 159, 161, 163, 165, 167, 169, 171, 173, 175, 177, 179, 181, 183, 185, 187, 189, 191, 193, 324, 326, 328, 330, 332, 334, 336, 338, 340, 342, 344, 348, 350, 352, 354, 356, 358, 360, 362, 364, 366, 368, 370, 372, 374, 376, 378, 380, 382, 384, 386, 560, 562, 564, 566, 568, 570, 572, 574, 576, 578, 580, 582, 584, 586, 588, 590**
출처 페이지 및 시험 방법 AISI: Typical Magnetic Properties · 시험 조건은 출처 참조
시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343), rolling-direction specimens, stress-relief annealed; AISI section.

PDF 6페이지 · **데이터 행 309**
출처 페이지 및 시험 방법 JGH CORE: Grades and Specifications · 시험 조건은 출처 참조
시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed. As printed: the published typical point is 0.01 W/kg above the separate maximum specification at this setting. Confirm the applicable guarantee with the mill.

PDF 8페이지 · **데이터 행 310**
출처 페이지 및 시험 방법 JGH CORE: Typical Electrical and Magnetic Properties · 시험 조건은 출처 참조
시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343); specimens sheared parallel to rolling direction and stress-relief annealed. As printed: the published typical point is 0.01 W/kg above the separate maximum specification at this setting. Confirm the applicable guarantee with the mill.

PDF 10페이지 · **데이터 행 345**
출처 페이지 및 시험 방법 AISI: Grades and Specifications · 시험 조건은 출처 참조
시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343), rolling-direction specimens, stress-relief annealed; AISI section. As printed: the published typical point is 0.01 W/kg above the separate maximum specification at this setting. Confirm the applicable guarantee with the mill.

PDF 11페이지 · **데이터 행 346**
출처 페이지 및 시험 방법 AISI: Typical Magnetic Properties · 시험 조건은 출처 참조
시험 조건 설명(영어) JIS C 2550-1:2011 (practically the same as ASTM A343), rolling-direction specimens, stress-relief annealed; AISI section. As printed: the published typical point is 0.01 W/kg above the separate maximum specification at this setting. Confirm the applicable guarantee with the mill.

독립 편집

Chenfan Electric이 철강사 공개 자료를 바탕으로 독립적으로 편집했습니다. 제조사의 승인을 받은 자료가 아닙니다.
인수 기준은 철강사 사양서와 서면 주문 조건에 따릅니다. 대표값과 참고값은 평가용입니다.

강대 데이터는 기술 검토용입니다. 완성 철심의 철손은 별도로 검증해야 합니다.
개정 정보 2026-11-14.2