Shougang

制造商牌号资料

资料摘要

牌号数据表数	65
原厂公布的数值记录	522
已公布频率	50 Hz / 60 Hz
公布的磁通密度范围	1.5-1.7 T
不同磁通密度点数	2

50 Hz 性能

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
1	**15SQH085** Shougang	0.15	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.60** W/kg	公开参考值
2	**15SQH085** Shougang	0.15	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.82** W/kg	典型值
3	**18SQG075** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.55** W/kg	公开参考值
4	**18SQG075** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.75** W/kg	保证上限
5	**18SQG075** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.74** W/kg	典型值
6	**18SQG080** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.58** W/kg	公开参考值
7	**18SQG080** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	保证上限
8	**18SQG080** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.79** W/kg	典型值
9	**18SQG085** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.61** W/kg	公开参考值
10	**18SQG085** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	保证上限
11	**18SQG085** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
12	**18SQG090** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.64** W/kg	公开参考值
13	**18SQG090** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	保证上限
14	**18SQG090** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.87** W/kg	典型值
15	**18SQGD060** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.44** W/kg	公开参考值
16	**18SQGD060** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.60** W/kg	保证上限
17	**18SQGD060** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.59** W/kg	典型值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
18	**18SQGD060LN** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.44** W/kg	公开参考值
19	**18SQGD060LN** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.59** W/kg	典型值
20	**18SQGD065** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.46** W/kg	公开参考值
21	**18SQGD065** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.65** W/kg	保证上限
22	**18SQGD065** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.64** W/kg	典型值
23	**18SQGD065LN** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.46** W/kg	公开参考值
24	**18SQGD065LN** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.64** W/kg	典型值
25	**18SQGD070** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.49** W/kg	公开参考值
26	**18SQGD070** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.70** W/kg	保证上限
27	**18SQGD070** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.68** W/kg	典型值
28	**18SQGD075** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.52** W/kg	公开参考值
29	**18SQGD075** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.75** W/kg	保证上限
30	**18SQGD075** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.73** W/kg	典型值
31	**18SQH085** Shougang	0.18	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.61** W/kg	公开参考值
32	**18SQH085** Shougang	0.18	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
33	**20SQG075** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.56** W/kg	公开参考值
34	**20SQG075** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.75** W/kg	保证上限
35	**20SQG075** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.74** W/kg	典型值
36	**20SQG080** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.59** W/kg	公开参考值
37	**20SQG080** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	保证上限
38	**20SQG080** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.79** W/kg	典型值
39	**20SQG085** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.61** W/kg	公开参考值
40	**20SQG085** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	保证上限
41	**20SQG085** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
42	**20SQG090** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.63** W/kg	公开参考值
43	**20SQG090** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	保证上限
44	**20SQG090** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.87** W/kg	典型值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
45	**20SQG095** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.65** W/kg	公开参考值
46	**20SQG095** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	保证上限
47	**20SQG095** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.92** W/kg	典型值
48	**20SQGD060** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.44** W/kg	公开参考值
49	**20SQGD060** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.60** W/kg	保证上限
50	**20SQGD060** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.59** W/kg	典型值
51	**20SQGD065** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.48** W/kg	公开参考值
52	**20SQGD065** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.65** W/kg	保证上限
53	**20SQGD065** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.64** W/kg	典型值
54	**20SQGD065LN** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.48** W/kg	公开参考值
55	**20SQGD065LN** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.64** W/kg	典型值
56	**20SQGD070** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.50** W/kg	公开参考值
57	**20SQGD070** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.70** W/kg	保证上限
58	**20SQGD070** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.68** W/kg	典型值
59	**20SQGD070DCR** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.50** W/kg	公开参考值
60	**20SQGD070DCR** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.68** W/kg	典型值
61	**20SQGD070LN** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.50** W/kg	公开参考值
62	**20SQGD070LN** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.68** W/kg	典型值
63	**20SQGD070LS** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.50** W/kg	公开参考值
64	**20SQGD070LS** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.68** W/kg	典型值
65	**20SQGD075** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.52** W/kg	公开参考值
66	**20SQGD075** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.75** W/kg	保证上限
67	**20SQGD075** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.72** W/kg	典型值
68	**20SQGD075LN** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.52** W/kg	公开参考值
69	**20SQGD075LN** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.72** W/kg	典型值
70	**20SQGD075LS** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.52** W/kg	公开参考值
71	**20SQGD075LS** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.72** W/kg	典型值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
72	**20SQGD080** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.55** W/kg	公开参考值
73	**20SQGD080** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	保证上限
74	**20SQGD080** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.77** W/kg	典型值
75	**20SQH085** Shougang	0.20	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.61** W/kg	公开参考值
76	**20SQH085** Shougang	0.20	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
77	**23SQG080** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.60** W/kg	公开参考值
78	**23SQG080** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	保证上限
79	**23SQG080** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	典型值
80	**23SQG085** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.62** W/kg	公开参考值
81	**23SQG085** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	保证上限
82	**23SQG085** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
83	**23SQG090** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.64** W/kg	公开参考值
84	**23SQG090** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	保证上限
85	**23SQG090** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	典型值
86	**23SQG095** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.66** W/kg	公开参考值
87	**23SQG095** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	保证上限
88	**23SQG095** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.88** W/kg	典型值
89	**23SQG100** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.67** W/kg	公开参考值
90	**23SQG100** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.00** W/kg	保证上限
91	**23SQG100** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.92** W/kg	典型值
92	**23SQGD070** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.53** W/kg	公开参考值
93	**23SQGD070** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.70** W/kg	保证上限
94	**23SQGD070** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.70** W/kg	典型值
95	**23SQGD075** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.55** W/kg	公开参考值
96	**23SQGD075** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.75** W/kg	保证上限
97	**23SQGD075** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.73** W/kg	典型值
98	**23SQGD080** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.56** W/kg	公开参考值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
99	**23SQGD080** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	保证上限
100	**23SQGD080** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.75** W/kg	典型值
101	**23SQGD080DCR** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.56** W/kg	公开参考值
102	**23SQGD080DCR** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.75** W/kg	典型值
103	**23SQGD080LN** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.56** W/kg	公开参考值
104	**23SQGD080LN** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.75** W/kg	典型值
105	**23SQGD080LS** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.57** W/kg	公开参考值
106	**23SQGD080LS** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.76** W/kg	典型值
107	**23SQGD085** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.59** W/kg	公开参考值
108	**23SQGD085** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	保证上限
109	**23SQGD085** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	典型值
110	**23SQGD085LN** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.59** W/kg	公开参考值
111	**23SQGD085LN** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	典型值
112	**23SQGD085LS** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.59** W/kg	公开参考值
113	**23SQGD085LS** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	典型值
114	**23SQGD090** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.62** W/kg	公开参考值
115	**23SQGD090** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	保证上限
116	**23SQGD090** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	典型值
117	**23SQH090** Shougang	0.23	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.64** W/kg	公开参考值
118	**23SQH090** Shougang	0.23	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	典型值
119	**27SQG090** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.67** W/kg	公开参考值
120	**27SQG090** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	保证上限
121	**27SQG090** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.89** W/kg	典型值
122	**27SQG095** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.68** W/kg	公开参考值
123	**27SQG095** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	保证上限
124	**27SQG095** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.92** W/kg	典型值
125	**27SQG100** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.69** W/kg	公开参考值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
126	**27SQG100** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.00** W/kg	保证上限
127	**27SQG100** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	典型值
128	**27SQG110** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.70** W/kg	公开参考值
129	**27SQG110** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.10** W/kg	保证上限
130	**27SQG110** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.00** W/kg	典型值
131	**27SQGD080** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.61** W/kg	公开参考值
132	**27SQGD080** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	保证上限
133	**27SQGD080** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.80** W/kg	典型值
134	**27SQGD085** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.62** W/kg	公开参考值
135	**27SQGD085** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	保证上限
136	**27SQGD085** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
137	**27SQGD085DCR** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.62** W/kg	公开参考值
138	**27SQGD085DCR** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
139	**27SQGD085LN** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.62** W/kg	公开参考值
140	**27SQGD085LN** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
141	**27SQGD090** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.62** W/kg	公开参考值
142	**27SQGD090** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	保证上限
143	**27SQGD090** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	典型值
144	**27SQGD090LN** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.62** W/kg	公开参考值
145	**27SQGD090LN** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.85** W/kg	典型值
146	**27SQGD095** Shougang	0.27	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.64** W/kg	公开参考值
147	**27SQGD095** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	保证上限
148	**27SQGD095** Shougang	0.27	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	典型值
149	**30SQG095** Shougang	0.30	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.72** W/kg	公开参考值
150	**30SQG095** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	保证上限
151	**30SQG095** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	典型值
152	**30SQG100** Shougang	0.30	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.73** W/kg	公开参考值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
153	**30SQG100** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.00** W/kg	保证上限
154	**30SQG100** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.97** W/kg	典型值
155	**30SQG105** Shougang	0.30	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.74** W/kg	公开参考值
156	**30SQG105** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.05** W/kg	保证上限
157	**30SQG105** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.00** W/kg	典型值
158	**30SQG120** Shougang	0.30	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.77** W/kg	公开参考值
159	**30SQG120** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.20** W/kg	保证上限
160	**30SQG120** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.04** W/kg	典型值
161	**30SQGD090** Shougang	0.30	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.67** W/kg	公开参考值
162	**30SQGD090** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	保证上限
163	**30SQGD090** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	典型值
164	**30SQGD095** Shougang	0.30	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.69** W/kg	公开参考值
165	**30SQGD095** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	保证上限
166	**30SQGD095** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.91** W/kg	典型值
167	**30SQGD100** Shougang	0.30	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.71** W/kg	公开参考值
168	**30SQGD100** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.00** W/kg	保证上限
169	**30SQGD100** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	典型值
170	**30SQGD100LN** Shougang	0.30	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.71** W/kg	公开参考值
171	**30SQGD100LN** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	典型值
172	**30SQGD105** Shougang	0.30	比总损耗	50 Hz / 1.5 T 原厂未注明 B 或 J	**0.73** W/kg	公开参考值
173	**30SQGD105** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**1.05** W/kg	保证上限
174	**30SQGD105** Shougang	0.30	比总损耗	50 Hz / 1.7 T 原厂未注明 B 或 J	**0.98** W/kg	典型值

60 Hz 性能

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
175	**15SQH085** Shougang	0.15	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.78** W/kg	公开参考值
176	**15SQH085** Shougang	0.15	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.07** W/kg	典型值
177	**18SQG075** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.73** W/kg	公开参考值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
178	**18SQG075** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.96** W/kg	典型值
179	**18SQG080** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.76** W/kg	公开参考值
180	**18SQG080** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.02** W/kg	典型值
181	**18SQG085** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.79** W/kg	公开参考值
182	**18SQG085** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.08** W/kg	典型值
183	**18SQG090** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.85** W/kg	公开参考值
184	**18SQG090** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.19** W/kg	典型值
185	**18SQGD060** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.58** W/kg	公开参考值
186	**18SQGD060** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.77** W/kg	典型值
187	**18SQGD060LN** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.58** W/kg	公开参考值
188	**18SQGD060LN** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.77** W/kg	典型值
189	**18SQGD065** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.62** W/kg	公开参考值
190	**18SQGD065** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
191	**18SQGD065LN** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.62** W/kg	公开参考值
192	**18SQGD065LN** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.83** W/kg	典型值
193	**18SQGD070** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.65** W/kg	公开参考值
194	**18SQGD070** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.90** W/kg	典型值
195	**18SQGD075** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.67** W/kg	公开参考值
196	**18SQGD075** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.93** W/kg	典型值
197	**18SQH085** Shougang	0.18	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.79** W/kg	公开参考值
198	**18SQH085** Shougang	0.18	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.08** W/kg	典型值
199	**20SQG075** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.73** W/kg	公开参考值
200	**20SQG075** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.96** W/kg	典型值
201	**20SQG080** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.77** W/kg	公开参考值
202	**20SQG080** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.03** W/kg	典型值
203	**20SQG085** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.8** W/kg	公开参考值
204	**20SQG085** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.08** W/kg	典型值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
205	**20SQG090** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.82** W/kg	公开参考值
206	**20SQG090** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.12** W/kg	典型值
207	**20SQG095** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.85** W/kg	公开参考值
208	**20SQG095** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.19** W/kg	典型值
209	**20SQGD060** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.59** W/kg	公开参考值
210	**20SQGD060** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.75** W/kg	典型值
211	**20SQGD065** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.63** W/kg	公开参考值
212	**20SQGD065** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.84** W/kg	典型值
213	**20SQGD065LN** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.63** W/kg	公开参考值
214	**20SQGD065LN** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.84** W/kg	典型值
215	**20SQGD070** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.66** W/kg	公开参考值
216	**20SQGD070** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.89** W/kg	典型值
217	**20SQGD070DCR** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.66** W/kg	公开参考值
218	**20SQGD070DCR** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.89** W/kg	典型值
219	**20SQGD070LN** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.66** W/kg	公开参考值
220	**20SQGD070LN** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.89** W/kg	典型值
221	**20SQGD070LS** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.66** W/kg	公开参考值
222	**20SQGD070LS** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.89** W/kg	典型值
223	**20SQGD075** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.69** W/kg	公开参考值
224	**20SQGD075** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	典型值
225	**20SQGD075LN** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.69** W/kg	公开参考值
226	**20SQGD075LN** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	典型值
227	**20SQGD075LS** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.69** W/kg	公开参考值
228	**20SQGD075LS** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.95** W/kg	典型值
229	**20SQGD080** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.72** W/kg	公开参考值
230	**20SQGD080** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.99** W/kg	典型值
231	**20SQH085** Shougang	0.20	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.8** W/kg	公开参考值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
232	**20SQH085** Shougang	0.20	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.08** W/kg	典型值
233	**23SQG080** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.79** W/kg	公开参考值
234	**23SQG080** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.05** W/kg	典型值
235	**23SQG085** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.81** W/kg	公开参考值
236	**23SQG085** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.09** W/kg	典型值
237	**23SQG090** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.84** W/kg	公开参考值
238	**23SQG090** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.12** W/kg	典型值
239	**23SQG095** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.86** W/kg	公开参考值
240	**23SQG095** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.16** W/kg	典型值
241	**23SQG100** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.88** W/kg	公开参考值
242	**23SQG100** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.21** W/kg	典型值
243	**23SQGD070** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.71** W/kg	公开参考值
244	**23SQGD070** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.93** W/kg	典型值
245	**23SQGD075** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.73** W/kg	公开参考值
246	**23SQGD075** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**0.97** W/kg	典型值
247	**23SQGD080** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.75** W/kg	公开参考值
248	**23SQGD080** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.01** W/kg	典型值
249	**23SQGD080DCR** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.75** W/kg	公开参考值
250	**23SQGD080DCR** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.01** W/kg	典型值
251	**23SQGD080LN** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.75** W/kg	公开参考值
252	**23SQGD080LN** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.01** W/kg	典型值
253	**23SQGD080LS** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.76** W/kg	公开参考值
254	**23SQGD080LS** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.02** W/kg	典型值
255	**23SQGD085** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.78** W/kg	公开参考值
256	**23SQGD085** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.04** W/kg	典型值
257	**23SQGD085LN** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.78** W/kg	公开参考值
258	**23SQGD085LN** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.04** W/kg	典型值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
259	**23SQGD085LS** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.78** W/kg	公开参考值
260	**23SQGD085LS** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.04** W/kg	典型值
261	**23SQGD090** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.81** W/kg	公开参考值
262	**23SQGD090** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.11** W/kg	典型值
263	**23SQH090** Shougang	0.23	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.84** W/kg	公开参考值
264	**23SQH090** Shougang	0.23	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.12** W/kg	典型值
265	**27SQG090** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.88** W/kg	公开参考值
266	**27SQG090** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.18** W/kg	典型值
267	**27SQG095** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.91** W/kg	公开参考值
268	**27SQG095** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.22** W/kg	典型值
269	**27SQG100** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.91** W/kg	公开参考值
270	**27SQG100** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.23** W/kg	典型值
271	**27SQG110** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.93** W/kg	公开参考值
272	**27SQG110** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.27** W/kg	典型值
273	**27SQGD080** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.80** W/kg	公开参考值
274	**27SQGD080** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.06** W/kg	典型值
275	**27SQGD085** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.82** W/kg	公开参考值
276	**27SQGD085** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.10** W/kg	典型值
277	**27SQGD085DCR** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.82** W/kg	公开参考值
278	**27SQGD085DCR** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.10** W/kg	典型值
279	**27SQGD085LN** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.82** W/kg	公开参考值
280	**27SQGD085LN** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.10** W/kg	典型值
281	**27SQGD090** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.84** W/kg	公开参考值
282	**27SQGD090** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.12** W/kg	典型值
283	**27SQGD090LN** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.84** W/kg	公开参考值
284	**27SQGD090LN** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.12** W/kg	典型值
285	**27SQGD095** Shougang	0.27	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.87** W/kg	公开参考值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
286	**27SQGD095** Shougang	0.27	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.16** W/kg	典型值
287	**30SQG095** Shougang	0.30	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.96** W/kg	公开参考值
288	**30SQG095** Shougang	0.30	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.26** W/kg	典型值
289	**30SQG100** Shougang	0.30	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.98** W/kg	公开参考值
290	**30SQG100** Shougang	0.30	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.29** W/kg	典型值
291	**30SQG105** Shougang	0.30	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.99** W/kg	公开参考值
292	**30SQG105** Shougang	0.30	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.30** W/kg	典型值
293	**30SQG120** Shougang	0.30	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.99** W/kg	公开参考值
294	**30SQG120** Shougang	0.30	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.36** W/kg	典型值
295	**30SQGD090** Shougang	0.30	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.90** W/kg	公开参考值
296	**30SQGD090** Shougang	0.30	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.19** W/kg	典型值
297	**30SQGD095** Shougang	0.30	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.92** W/kg	公开参考值
298	**30SQGD095** Shougang	0.30	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.22** W/kg	典型值
299	**30SQGD100** Shougang	0.30	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.93** W/kg	公开参考值
300	**30SQGD100** Shougang	0.30	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.23** W/kg	典型值
301	**30SQGD100LN** Shougang	0.30	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.93** W/kg	公开参考值
302	**30SQGD100LN** Shougang	0.30	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.23** W/kg	典型值
303	**30SQGD105** Shougang	0.30	比总损耗	60 Hz / 1.5 T 原厂未注明 B 或 J	**0.97** W/kg	公开参考值
304	**30SQGD105** Shougang	0.30	比总损耗	60 Hz / 1.7 T 原厂未注明 B 或 J	**1.28** W/kg	典型值

其他性能

原厂未单列频率

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
305	**15SQH085** Shougang	0.15	磁极化强度	H = 800 A/m	**1.88** T	典型值
306	**15SQH085** Shougang	0.15	叠片系数	-	**0.940** 无量纲	典型值
307	**18SQG075** Shougang	0.18	磁极化强度	H = 800 A/m	**1.89** T	保证下限
308	**18SQG075** Shougang	0.18	磁极化强度	H = 800 A/m	**1.90** T	典型值
309	**18SQG075** Shougang	0.18	叠片系数	-	**0.955** 无量纲	保证下限

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
310	**18SQG075** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
311	**18SQG080** Shougang	0.18	磁极化强度	H = 800 A/m	**1.88** T	保证下限
312	**18SQG080** Shougang	0.18	磁极化强度	H = 800 A/m	**1.90** T	典型值
313	**18SQG080** Shougang	0.18	叠片系数	-	**0.955** 无量纲	保证下限
314	**18SQG080** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
315	**18SQG085** Shougang	0.18	磁极化强度	H = 800 A/m	**1.88** T	保证下限
316	**18SQG085** Shougang	0.18	磁极化强度	H = 800 A/m	**1.89** T	典型值
317	**18SQG085** Shougang	0.18	叠片系数	-	**0.955** 无量纲	保证下限
318	**18SQG085** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
319	**18SQG090** Shougang	0.18	磁极化强度	H = 800 A/m	**1.88** T	保证下限
320	**18SQG090** Shougang	0.18	磁极化强度	H = 800 A/m	**1.88** T	典型值
321	**18SQG090** Shougang	0.18	叠片系数	-	**0.955** 无量纲	保证下限
322	**18SQG090** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
323	**18SQGD060** Shougang	0.18	磁极化强度	H = 800 A/m	**1.88** T	保证下限
324	**18SQGD060** Shougang	0.18	磁极化强度	H = 800 A/m	**1.91** T	典型值
325	**18SQGD060** Shougang	0.18	叠片系数	-	**0.955** 无量纲	保证下限
326	**18SQGD060** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
327	**18SQGD060LN** Shougang	0.18	磁极化强度	H = 800 A/m	**1.91** T	典型值
328	**18SQGD060LN** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
329	**18SQGD065** Shougang	0.18	磁极化强度	H = 800 A/m	**1.88** T	保证下限
330	**18SQGD065** Shougang	0.18	磁极化强度	H = 800 A/m	**1.91** T	典型值
331	**18SQGD065** Shougang	0.18	叠片系数	-	**0.955** 无量纲	保证下限
332	**18SQGD065** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
333	**18SQGD065LN** Shougang	0.18	磁极化强度	H = 800 A/m	**1.91** T	典型值
334	**18SQGD065LN** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
335	**18SQGD070** Shougang	0.18	磁极化强度	H = 800 A/m	**1.88** T	保证下限
336	**18SQGD070** Shougang	0.18	磁极化强度	H = 800 A/m	**1.90** T	典型值
337	**18SQGD070** Shougang	0.18	叠片系数	-	**0.955** 无量纲	保证下限

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
338	**18SQGD070** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
339	**18SQGD075** Shougang	0.18	磁极化强度	H = 800 A/m	**1.88** T	保证下限
340	**18SQGD075** Shougang	0.18	磁极化强度	H = 800 A/m	**1.88** T	典型值
341	**18SQGD075** Shougang	0.18	叠片系数	-	**0.955** 无量纲	保证下限
342	**18SQGD075** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
343	**18SQH085** Shougang	0.18	磁极化强度	H = 800 A/m	**1.89** T	典型值
344	**18SQH085** Shougang	0.18	叠片系数	-	**0.955** 无量纲	典型值
345	**20SQG075** Shougang	0.20	磁极化强度	H = 800 A/m	**1.89** T	保证下限
346	**20SQG075** Shougang	0.20	磁极化强度	H = 800 A/m	**1.91** T	典型值
347	**20SQG075** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
348	**20SQG075** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
349	**20SQG080** Shougang	0.20	磁极化强度	H = 800 A/m	**1.89** T	保证下限
350	**20SQG080** Shougang	0.20	磁极化强度	H = 800 A/m	**1.90** T	典型值
351	**20SQG080** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
352	**20SQG080** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
353	**20SQG085** Shougang	0.20	磁极化强度	H = 800 A/m	**1.88** T	保证下限
354	**20SQG085** Shougang	0.20	磁极化强度	H = 800 A/m	**1.90** T	典型值
355	**20SQG085** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
356	**20SQG085** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
357	**20SQG090** Shougang	0.20	磁极化强度	H = 800 A/m	**1.88** T	保证下限
358	**20SQG090** Shougang	0.20	磁极化强度	H = 800 A/m	**1.89** T	典型值
359	**20SQG090** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
360	**20SQG090** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
361	**20SQG095** Shougang	0.20	磁极化强度	H = 800 A/m	**1.88** T	保证下限
362	**20SQG095** Shougang	0.20	磁极化强度	H = 800 A/m	**1.88** T	典型值
363	**20SQG095** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
364	**20SQG095** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
365	**20SQGD060** Shougang	0.20	磁极化强度	H = 800 A/m	**1.89** T	保证下限

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
366	**20SQGD060** Shougang	0.20	磁极化强度	H = 800 A/m	**1.92** T	典型值
367	**20SQGD060** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
368	**20SQGD060** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
369	**20SQGD065** Shougang	0.20	磁极化强度	H = 800 A/m	**1.89** T	保证下限
370	**20SQGD065** Shougang	0.20	磁极化强度	H = 800 A/m	**1.92** T	典型值
371	**20SQGD065** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
372	**20SQGD065** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
373	**20SQGD065LN** Shougang	0.20	磁极化强度	H = 800 A/m	**1.92** T	典型值
374	**20SQGD065LN** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
375	**20SQGD070** Shougang	0.20	磁极化强度	H = 800 A/m	**1.89** T	保证下限
376	**20SQGD070** Shougang	0.20	磁极化强度	H = 800 A/m	**1.91** T	典型值
377	**20SQGD070** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
378	**20SQGD070** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
379	**20SQGD070DCR** Shougang	0.20	磁极化强度	H = 800 A/m	**1.91** T	典型值
380	**20SQGD070DCR** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
381	**20SQGD070LN** Shougang	0.20	磁极化强度	H = 800 A/m	**1.91** T	典型值
382	**20SQGD070LN** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
383	**20SQGD070LS** Shougang	0.20	磁极化强度	H = 800 A/m	**1.91** T	典型值
384	**20SQGD070LS** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
385	**20SQGD075** Shougang	0.20	磁极化强度	H = 800 A/m	**1.88** T	保证下限
386	**20SQGD075** Shougang	0.20	磁极化强度	H = 800 A/m	**1.91** T	典型值
387	**20SQGD075** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
388	**20SQGD075** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
389	**20SQGD075LN** Shougang	0.20	磁极化强度	H = 800 A/m	**1.91** T	典型值
390	**20SQGD075LN** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
391	**20SQGD075LS** Shougang	0.20	磁极化强度	H = 800 A/m	**1.91** T	典型值
392	**20SQGD075LS** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
393	**20SQGD080** Shougang	0.20	磁极化强度	H = 800 A/m	**1.88** T	保证下限

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
394	**20SQGD080** Shougang	0.20	磁极化强度	H = 800 A/m	**1.89** T	典型值
395	**20SQGD080** Shougang	0.20	叠片系数	-	**0.955** 无量纲	保证下限
396	**20SQGD080** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
397	**20SQH085** Shougang	0.20	磁极化强度	H = 800 A/m	**1.90** T	典型值
398	**20SQH085** Shougang	0.20	叠片系数	-	**0.955** 无量纲	典型值
399	**23SQG080** Shougang	0.23	磁极化强度	H = 800 A/m	**1.89** T	保证下限
400	**23SQG080** Shougang	0.23	磁极化强度	H = 800 A/m	**1.92** T	典型值
401	**23SQG080** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限
402	**23SQG080** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
403	**23SQG085** Shougang	0.23	磁极化强度	H = 800 A/m	**1.89** T	保证下限
404	**23SQG085** Shougang	0.23	磁极化强度	H = 800 A/m	**1.92** T	典型值
405	**23SQG085** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限
406	**23SQG085** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
407	**23SQG090** Shougang	0.23	磁极化强度	H = 800 A/m	**1.89** T	保证下限
408	**23SQG090** Shougang	0.23	磁极化强度	H = 800 A/m	**1.91** T	典型值
409	**23SQG090** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限
410	**23SQG090** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
411	**23SQG095** Shougang	0.23	磁极化强度	H = 800 A/m	**1.88** T	保证下限
412	**23SQG095** Shougang	0.23	磁极化强度	H = 800 A/m	**1.91** T	典型值
413	**23SQG095** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限
414	**23SQG095** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
415	**23SQG100** Shougang	0.23	磁极化强度	H = 800 A/m	**1.88** T	保证下限
416	**23SQG100** Shougang	0.23	磁极化强度	H = 800 A/m	**1.91** T	典型值
417	**23SQG100** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限
418	**23SQG100** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
419	**23SQGD070** Shougang	0.23	磁极化强度	H = 800 A/m	**1.89** T	保证下限
420	**23SQGD070** Shougang	0.23	磁极化强度	H = 800 A/m	**1.92** T	典型值
421	**23SQGD070** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
422	**23SQGD070** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
423	**23SQGD075** Shougang	0.23	磁极化强度	H = 800 A/m	**1.89** T	保证下限
424	**23SQGD075** Shougang	0.23	磁极化强度	H = 800 A/m	**1.92** T	典型值
425	**23SQGD075** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限
426	**23SQGD075** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
427	**23SQGD080** Shougang	0.23	磁极化强度	H = 800 A/m	**1.89** T	保证下限
428	**23SQGD080** Shougang	0.23	磁极化强度	H = 800 A/m	**1.92** T	典型值
429	**23SQGD080** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限
430	**23SQGD080** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
431	**23SQGD080DCR** Shougang	0.23	磁极化强度	H = 800 A/m	**1.92** T	典型值
432	**23SQGD080DCR** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
433	**23SQGD080LN** Shougang	0.23	磁极化强度	H = 800 A/m	**1.93** T	典型值
434	**23SQGD080LN** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
435	**23SQGD080LS** Shougang	0.23	磁极化强度	H = 800 A/m	**1.92** T	典型值
436	**23SQGD080LS** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
437	**23SQGD085** Shougang	0.23	磁极化强度	H = 800 A/m	**1.89** T	保证下限
438	**23SQGD085** Shougang	0.23	磁极化强度	H = 800 A/m	**1.91** T	典型值
439	**23SQGD085** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限
440	**23SQGD085** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
441	**23SQGD085LN** Shougang	0.23	磁极化强度	H = 800 A/m	**1.92** T	典型值
442	**23SQGD085LN** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
443	**23SQGD085LS** Shougang	0.23	磁极化强度	H = 800 A/m	**1.91** T	典型值
444	**23SQGD085LS** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
445	**23SQGD090** Shougang	0.23	磁极化强度	H = 800 A/m	**1.88** T	保证下限
446	**23SQGD090** Shougang	0.23	磁极化强度	H = 800 A/m	**1.90** T	典型值
447	**23SQGD090** Shougang	0.23	叠片系数	-	**0.955** 无量纲	保证下限
448	**23SQGD090** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
449	**23SQH090** Shougang	0.23	磁极化强度	H = 800 A/m	**1.91** T	典型值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
450	**23SQH090** Shougang	0.23	叠片系数	-	**0.955** 无量纲	典型值
451	**27SQG090** Shougang	0.27	磁极化强度	H = 800 A/m	**1.88** T	保证下限
452	**27SQG090** Shougang	0.27	磁极化强度	H = 800 A/m	**1.91** T	典型值
453	**27SQG090** Shougang	0.27	叠片系数	-	**0.960** 无量纲	保证下限
454	**27SQG090** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
455	**27SQG095** Shougang	0.27	磁极化强度	H = 800 A/m	**1.88** T	保证下限
456	**27SQG095** Shougang	0.27	磁极化强度	H = 800 A/m	**1.91** T	典型值
457	**27SQG095** Shougang	0.27	叠片系数	-	**0.960** 无量纲	保证下限
458	**27SQG095** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
459	**27SQG100** Shougang	0.27	磁极化强度	H = 800 A/m	**1.88** T	保证下限
460	**27SQG100** Shougang	0.27	磁极化强度	H = 800 A/m	**1.91** T	典型值
461	**27SQG100** Shougang	0.27	叠片系数	-	**0.960** 无量纲	保证下限
462	**27SQG100** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
463	**27SQG110** Shougang	0.27	磁极化强度	H = 800 A/m	**1.88** T	保证下限
464	**27SQG110** Shougang	0.27	磁极化强度	H = 800 A/m	**1.90** T	典型值
465	**27SQG110** Shougang	0.27	叠片系数	-	**0.960** 无量纲	保证下限
466	**27SQG110** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
467	**27SQGD080** Shougang	0.27	磁极化强度	H = 800 A/m	**1.88** T	保证下限
468	**27SQGD080** Shougang	0.27	磁极化强度	H = 800 A/m	**1.91** T	典型值
469	**27SQGD080** Shougang	0.27	叠片系数	-	**0.960** 无量纲	保证下限
470	**27SQGD080** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
471	**27SQGD085** Shougang	0.27	磁极化强度	H = 800 A/m	**1.88** T	保证下限
472	**27SQGD085** Shougang	0.27	磁极化强度	H = 800 A/m	**1.91** T	典型值
473	**27SQGD085** Shougang	0.27	叠片系数	-	**0.960** 无量纲	保证下限
474	**27SQGD085** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
475	**27SQGD085DCR** Shougang	0.27	磁极化强度	H = 800 A/m	**1.91** T	典型值
476	**27SQGD085DCR** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
477	**27SQGD085LN** Shougang	0.27	磁极化强度	H = 800 A/m	**1.91** T	典型值

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
478	**27SQGD085LN** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
479	**27SQGD090** Shougang	0.27	磁极化强度	H = 800 A/m	**1.88** T	保证下限
480	**27SQGD090** Shougang	0.27	磁极化强度	H = 800 A/m	**1.91** T	典型值
481	**27SQGD090** Shougang	0.27	叠片系数	-	**0.960** 无量纲	保证下限
482	**27SQGD090** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
483	**27SQGD090LN** Shougang	0.27	磁极化强度	H = 800 A/m	**1.91** T	典型值
484	**27SQGD090LN** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
485	**27SQGD095** Shougang	0.27	磁极化强度	H = 800 A/m	**1.88** T	保证下限
486	**27SQGD095** Shougang	0.27	磁极化强度	H = 800 A/m	**1.90** T	典型值
487	**27SQGD095** Shougang	0.27	叠片系数	-	**0.960** 无量纲	保证下限
488	**27SQGD095** Shougang	0.27	叠片系数	-	**0.960** 无量纲	典型值
489	**30SQG095** Shougang	0.30	磁极化强度	H = 800 A/m	**1.88** T	保证下限
490	**30SQG095** Shougang	0.30	磁极化强度	H = 800 A/m	**1.92** T	典型值
491	**30SQG095** Shougang	0.30	叠片系数	-	**0.960** 无量纲	保证下限
492	**30SQG095** Shougang	0.30	叠片系数	-	**0.965** 无量纲	典型值
493	**30SQG100** Shougang	0.30	磁极化强度	H = 800 A/m	**1.88** T	保证下限
494	**30SQG100** Shougang	0.30	磁极化强度	H = 800 A/m	**1.92** T	典型值
495	**30SQG100** Shougang	0.30	叠片系数	-	**0.960** 无量纲	保证下限
496	**30SQG100** Shougang	0.30	叠片系数	-	**0.965** 无量纲	典型值
497	**30SQG105** Shougang	0.30	磁极化强度	H = 800 A/m	**1.88** T	保证下限
498	**30SQG105** Shougang	0.30	磁极化强度	H = 800 A/m	**1.91** T	典型值
499	**30SQG105** Shougang	0.30	叠片系数	-	**0.960** 无量纲	保证下限
500	**30SQG105** Shougang	0.30	叠片系数	-	**0.965** 无量纲	典型值
501	**30SQG120** Shougang	0.30	磁极化强度	H = 800 A/m	**1.88** T	保证下限
502	**30SQG120** Shougang	0.30	磁极化强度	H = 800 A/m	**1.91** T	典型值
503	**30SQG120** Shougang	0.30	叠片系数	-	**0.960** 无量纲	保证下限
504	**30SQG120** Shougang	0.30	叠片系数	-	**0.965** 无量纲	典型值
505	**30SQGD090** Shougang	0.30	磁极化强度	H = 800 A/m	**1.88** T	保证下限

序号	制造商 / 牌号	厚度 mm	性能指标	试验点	数值	数值类别
506	**30SQGD090** Shougang	0.30	磁极化强度	H = 800 A/m	**1.91** T	典型值
507	**30SQGD090** Shougang	0.30	叠片系数	-	**0.960** 无量纲	保证下限
508	**30SQGD090** Shougang	0.30	叠片系数	-	**0.965** 无量纲	典型值
509	**30SQGD095** Shougang	0.30	磁极化强度	H = 800 A/m	**1.88** T	保证下限
510	**30SQGD095** Shougang	0.30	磁极化强度	H = 800 A/m	**1.91** T	典型值
511	**30SQGD095** Shougang	0.30	叠片系数	-	**0.960** 无量纲	保证下限
512	**30SQGD095** Shougang	0.30	叠片系数	-	**0.965** 无量纲	典型值
513	**30SQGD100** Shougang	0.30	磁极化强度	H = 800 A/m	**1.88** T	保证下限
514	**30SQGD100** Shougang	0.30	磁极化强度	H = 800 A/m	**1.90** T	典型值
515	**30SQGD100** Shougang	0.30	叠片系数	-	**0.960** 无量纲	保证下限
516	**30SQGD100** Shougang	0.30	叠片系数	-	**0.965** 无量纲	典型值
517	**30SQGD100LN** Shougang	0.30	磁极化强度	H = 800 A/m	**1.91** T	典型值
518	**30SQGD100LN** Shougang	0.30	叠片系数	-	**0.965** 无量纲	典型值
519	**30SQGD105** Shougang	0.30	磁极化强度	H = 800 A/m	**1.88** T	保证下限
520	**30SQGD105** Shougang	0.30	磁极化强度	H = 800 A/m	**1.89** T	典型值
521	**30SQGD105** Shougang	0.30	叠片系数	-	**0.960** 无量纲	保证下限
522	**30SQGD105** Shougang	0.30	叠片系数	-	**0.965** 无量纲	典型值

原厂资料与试验条件

按表号及数据序号查询原厂试验条件。

Shougang

Shougang Cold Rolled Grain-Oriented Electrical Steel Product Manual

版本 2025 catalogue (official catalogue label; PDF dated 2025-07-23) 打开原厂资料

PDF 第 9 页 · 数据序号 1, 31, 75, 117, 175, 197, 231, 263

来源页码与试验方法 §2.5 Table 8 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Footnote a designates the 1.5 T entry as a reference value.

PDF 第 9 页 · 数据序号 2, 32, 76, 118

来源页码与试验方法 §2.5 Table 8 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Listed in §2.5 typical-data table.

PDF 第 8 页 · 数据序号 3, 6, 9, 12, 33, 36, 39, 42, 45, 77, 80, 83, 86, 89, 119, 122, 125, 128, 149, 152, 155, 158, 177, 179, 181, 183, 199, 201, 203, 205, 207, 233, 235, 237, 239, 241, 265, 267, 269, 271, 287, 289, 291, 293

来源页码与试验方法 §2.5 Table 1 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Footnote a designates the 1.5 T entry as a reference value.

PDF 第 7 页 · 数据序号 4, 7, 10, 13, 34, 37, 40, 43, 46, 78, 81, 84, 87, 90, 120, 123, 126, 129, 150, 153, 156, 159

来源页码与试验方法 §2.4 Table 1 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated.

PDF 第 8 页 · 数据序号 5, 8, 11, 14, 35, 38, 41, 44, 47, 79, 82, 85, 88, 91, 121, 124, 127, 130, 151, 154, 157, 160

来源页码与试验方法 §2.5 Table 1 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Listed in §2.5 typical-data table.

PDF 第 8 页 · 数据序号 15, 20, 25, 28, 48, 51, 56, 65, 72, 92, 95, 98, 107, 114, 131, 134, 141, 146, 161, 164, 167, 172, 185, 189, 193, 195, 209, 211, 215, 223, 229, 243, 245, 247, 255, 261, 273, 275, 281, 285, 295, 297, 299, 303

来源页码与试验方法 §2.5 Table 2 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Footnote a designates the 1.5 T entry as a reference value.

PDF 第 7 页 · 数据序号 16, 21, 26, 29, 49, 52, 57, 66, 73, 93, 96, 99, 108, 115, 132, 135, 142, 147, 162, 165, 168, 173

来源页码与试验方法 §2.4 Table 2 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated.

PDF 第 8 页 · 数据序号 17, 22, 27, 30, 50, 53, 58, 67, 74, 94, 97, 100, 109, 116, 133, 136, 143, 148, 163, 166, 169, 174

来源页码与试验方法 §2.5 Table 2 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Listed in §2.5 typical-data table.

PDF 第 9 页 · 数据序号 18, 23, 54, 61, 68, 103, 110, 139, 144, 170, 187, 191, 213, 219, 225, 251, 257, 279, 283, 301

来源页码与试验方法 §2.5 Table 3 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Footnote a designates the 1.5 T entry as a reference value.

PDF 第 9 页 · 数据序号 19, 24, 55, 62, 69, 104, 111, 140, 145, 171
来源页码与试验方法 §2.5 Table 3 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Listed in §2.5 typical-data table.

PDF 第 9 页 · 数据序号 59, 101, 137, 217, 249, 277
来源页码与试验方法 §2.5 Table 7 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Footnote a designates the 1.5 T entry as a reference value.

PDF 第 9 页 · 数据序号 60, 102, 138
来源页码与试验方法 §2.5 Table 7 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Listed in §2.5 typical-data table.

PDF 第 9 页 · 数据序号 63, 70, 105, 112, 221, 227, 253, 259
来源页码与试验方法 §2.5 Table 4 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Footnote a designates the 1.5 T entry as a reference value.

PDF 第 9 页 · 数据序号 64, 71, 106, 113
来源页码与试验方法 §2.5 Table 4 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. Listed in §2.5 typical-data table.

PDF 第 9 页 · 数据序号 176, 198, 232, 264
来源页码与试验方法 §2.5 Table 8 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. §2.5 is a typical-data table. Footnote b says supply per P1.7/60 can be requested; confirm any guaranteed limit separately.

PDF 第 8 页 · 数据序号 178, 180, 182, 184, 200, 202, 204, 206, 208, 234, 236, 238, 240, 242, 266, 268, 270, 272, 288, 290, 292, 294
来源页码与试验方法 §2.5 Table 1 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. §2.5 is a typical-data table. Footnote b says supply per P1.7/60 can be requested; confirm any guaranteed limit separately.

PDF 第 8 页 · 数据序号 186, 190, 194, 196, 210, 212, 216, 224, 230, 244, 246, 248, 256, 262, 274, 276, 282, 286, 296, 298, 300, 304
来源页码与试验方法 §2.5 Table 2 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. §2.5 is a typical-data table. Footnote b says supply per P1.7/60 can be requested; confirm any guaranteed limit separately.

PDF 第 9 页 · 数据序号 188, 192, 214, 220, 226, 252, 258, 280, 284, 302
来源页码与试验方法 §2.5 Table 3 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. §2.5 is a typical-data table. Footnote b says supply per P1.7/60 can be requested; confirm any guaranteed limit separately.

PDF 第 9 页 · 数据序号 218, 250, 278
来源页码与试验方法 §2.5 Table 7 · 所引原厂表格未注明
试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. §2.5 is a typical-data table. Footnote b says supply per P1.7/60 can be requested; confirm any guaranteed limit separately.

PDF 第 9 页 · 数据序号 222, 228, 254, 260
来源页码与试验方法 §2.5 Table 4 · 所引原厂表格未注明

试验条件说明（英文） Producer reports P at the stated peak-density point and frequency; loss-table test fixture and explicit B/J basis are not stated. §2.5 is a typical-data table. Footnote b says supply per P1.7/60 can be requested; confirm any guaranteed limit separately.

PDF 第 9 页 · 数据序号 305, 343, 397, 449

来源页码与试验方法 §2.5 Table 8 · 所引原厂表格未注明

试验条件说明（英文） J800 at peak H=800 A/m. The table has a single value labelled 50 Hz or 60 Hz; no distinct frequency-specific values are reported.

PDF 第 9 页 · 数据序号 306, 344, 398, 450

来源页码与试验方法 §2.5 Table 8 · 所引原厂表格未注明

试验条件说明（英文） Dimensionless ratio for the steel strip; fixture is not specified.

PDF 第 7 页 · 数据序号 307, 311, 315, 319, 345, 349, 353, 357, 361, 399, 403, 407, 411, 415, 451, 455, 459, 463, 489, 493, 497, 501

来源页码与试验方法 §2.4 Table 1 · 所引原厂表格未注明

试验条件说明（英文） J800 at peak H=800 A/m. The table has a single value labelled 50 Hz or 60 Hz; no distinct frequency-specific values are reported.

PDF 第 8 页 · 数据序号 308, 312, 316, 320, 346, 350, 354, 358, 362, 400, 404, 408, 412, 416, 452, 456, 460, 464, 490, 494, 498, 502

来源页码与试验方法 §2.5 Table 1 · 所引原厂表格未注明

试验条件说明（英文） J800 at peak H=800 A/m. The table has a single value labelled 50 Hz or 60 Hz; no distinct frequency-specific values are reported.

PDF 第 7 页 · 数据序号 309, 313, 317, 321, 347, 351, 355, 359, 363, 401, 405, 409, 413, 417, 453, 457, 461, 465, 491, 495, 499, 503

来源页码与试验方法 §2.4 Table 1 · 所引原厂表格未注明

试验条件说明（英文） Dimensionless ratio for the steel strip; fixture is not specified.

PDF 第 8 页 · 数据序号 310, 314, 318, 322, 348, 352, 356, 360, 364, 402, 406, 410, 414, 418, 454, 458, 462, 466, 492, 496, 500, 504

来源页码与试验方法 §2.5 Table 1 · 所引原厂表格未注明

试验条件说明（英文） Dimensionless ratio for the steel strip; fixture is not specified.

PDF 第 7 页 · 数据序号 323, 329, 335, 339, 365, 369, 375, 385, 393, 419, 423, 427, 437, 445, 467, 471, 479, 485, 505, 509, 513, 519

来源页码与试验方法 §2.4 Table 2 · 所引原厂表格未注明

试验条件说明（英文） J800 at peak H=800 A/m. The table has a single value labelled 50 Hz or 60 Hz; no distinct frequency-specific values are reported.

PDF 第 8 页 · 数据序号 324, 330, 336, 340, 366, 370, 376, 386, 394, 420, 424, 428, 438, 446, 468, 472, 480, 486, 506, 510, 514, 520

来源页码与试验方法 §2.5 Table 2 · 所引原厂表格未注明

试验条件说明（英文） J800 at peak H=800 A/m. The table has a single value labelled 50 Hz or 60 Hz; no distinct frequency-specific values are reported.

PDF 第 7 页 · 数据序号 325, 331, 337, 341, 367, 371, 377, 387, 395, 421, 425, 429, 439, 447, 469, 473, 481, 487, 507, 511, 515, 521

来源页码与试验方法 §2.4 Table 2 · 所引原厂表格未注明

试验条件说明（英文） Dimensionless ratio for the steel strip; fixture is not specified.

PDF 第 8 页 · 数据序号 326, 332, 338, 342, 368, 372, 378, 388, 396, 422, 426, 430, 440, 448, 470, 474, 482, 488, 508, 512, 516, 522

来源页码与试验方法 §2.5 Table 2 · 所引原厂表格未注明

试验条件说明（英文） Dimensionless ratio for the steel strip; fixture is not specified.

PDF 第 9 页 · 数据序号 327, 333, 373, 381, 389, 433, 441, 477, 483, 517
来源页码与试验方法 §2.5 Table 3 · 所引原厂表格未注明
试验条件说明（英文） J800 at peak H=800 A/m. The table has a single value labelled 50 Hz or 60 Hz; no distinct frequency-specific values are reported.

PDF 第 9 页 · 数据序号 328, 334, 374, 382, 390, 434, 442, 478, 484, 518
来源页码与试验方法 §2.5 Table 3 · 所引原厂表格未注明
试验条件说明（英文） Dimensionless ratio for the steel strip; fixture is not specified.

PDF 第 9 页 · 数据序号 379, 431, 475
来源页码与试验方法 §2.5 Table 7 · 所引原厂表格未注明
试验条件说明（英文） J800 at peak H=800 A/m. The table has a single value labelled 50 Hz or 60 Hz; no distinct frequency-specific values are reported.

PDF 第 9 页 · 数据序号 380, 432, 476
来源页码与试验方法 §2.5 Table 7 · 所引原厂表格未注明
试验条件说明（英文） Dimensionless ratio for the steel strip; fixture is not specified.

PDF 第 9 页 · 数据序号 383, 391, 435, 443
来源页码与试验方法 §2.5 Table 4 · 所引原厂表格未注明
试验条件说明（英文） J800 at peak H=800 A/m. The table has a single value labelled 50 Hz or 60 Hz; no distinct frequency-specific values are reported.

PDF 第 9 页 · 数据序号 384, 392, 436, 444
来源页码与试验方法 §2.5 Table 4 · 所引原厂表格未注明
试验条件说明（英文） Dimensionless ratio for the steel strip; fixture is not specified.

独立汇编

宸帆电气根据钢厂公开数据独立整理。
按原厂技术规定及书面订单条件验收。典型值和参考值用于评估。
钢带数据供工程参考，成品铁芯损耗须另行验证。
版本 2026-11-14.2